



ipé
wood



cumaru
wood



garapa
wood

STEP OUT OF THE ORDINARY

PREMIUM DECKING

When it comes to building decks in North America, choosing the best decking wood is crucial for durability, aesthetics, and resistance to the harsh climate.

Exotic hardwood decking provides unparalleled beauty, strength, and longevity that perfectly complements our diverse landscapes and demanding weather conditions.



OLIVER LUMBER



ipé



DURABILITY

very resistant

JANKA HARDNESS

3,680 lbs.

BENDING STRENGTH

23,360 psi.

DENSITY

1.04g/cm³

Ipé is a hardwood from South America and undoubtedly the number one option for decking.

Known to last for 50 years, **Ipé** is extremely weather resistant, significantly harder, has superior bending strength, and has superb resistance to insects and decay.

When oiled and maintained, its natural gorgeous golden brown colour can darken to a deep reddish mahogany colour. **Ipé** can also be left to sun exposure without losing structural integrity and will gradually fade leaving a silvery grey patina.

cumaru



DURABILITY

very durable

JANKA HARDNESS

3,340 lbs.

BENDING STRENGTH

22,400 psi.

DENSITY

1.07 g/cm³

Cumaru has very similar characteristics to Ipé offering one of the best options in exotic wood decking.

Generally speaking, **Cumaru** is lighter in colour than Ipé and varies from yellow-brown to reddish brown, and with a grain that is more flamed. Similar to Ipé,

Cumaru can last 50 years with its superb durability and weathering properties, as well as resistance to termites and other dry-wood borers.

Unlike other exotic species, **Cumaru** does not emit tannin which tend to produce stains near swimming pools.

garapa



DURABILITY

high density

JANKA HARDNESS

1,630 lbs.

BENDING STRENGTH

12,900 psi.

DENSITY

.79 g/cm³

Garapa is an exotic hardwood that is naturally resistant to rot, decay and insect attack. Similar to Ipé and Cumaru, **Garapa** is naturally scratch resistant which allows the surface to remain smooth for many years, making **Garapa** a perfect wood for exterior decking.

When a lighter colour is preferred, **Garapa's** light golden honey colour

is iridescent when cut and matures to a rich brownish colour over time making it a great alternative to Ipé or Cumaru.

Garapa offers a 30 year lifespan with very low maintenance and is offered at a lower price point than Ipé and Cumaru.




OLIVER LUMBER

PREMIUM DECKING SOLUTIONS

These clips are the most affordable and easy to use fasteners for any decking.

EXTREME[®]
Gap Spacing 3/32" (2,4 mm)



Air-Dried Lumber & Composites

EXTREMES[®]
Gap Spacing 5/32" (4 mm)



Air-Dried, Kiln-Dried Lumber & Composites

EXTREMEKD[®]
Gap Spacing 1/4" (6,4 mm)





Kiln-Dried Lumber, Composites & PVC

Ipé
GOODFELLOW




Finish your premium hardwood decking with Ipé Oil to preserve its natural beauty and color. Apply approximately once per year, or up to twice a year if exposed to continuous direct sunlight.





Decking profiles available in 8' to 16' grooved or solid lengths.



The mark of
responsible forestry
FSC® C008114

Oliver Lumber is FSC®
certified.

Ask your Oliver Lumber
representative about
sourcing your premium
decking with FSC®
certification.

Extensive selection of
accessories available:

- Concealed fasteners
- Decorative post caps
- Installation lever
- Ipé plugs (for non-grooved boards)
- Ipé oil
- Cleaning and maintenance products
- Installation kits
- Screws



Call your Oliver Lumber representative who can help you
make the right choice for your unique decking project.



OLIVER LUMBER

oliverlumber.com

800-268-2471

